

CORIAN® SOLID SURFACE ADHESIVES

Introduction

This fabrication bulletin addresses adhesives and procedures used while fabricating Corian® Solid Surface.

Overview

There are several adhesive applications in the fabrication of Corian® Solid Surface.

An inconspicuous “hard” seam between two sheets of Corian® Solid Surface – Hard seams are essential to convert flat sheet into an object made from Corian® Solid Surface. DuPont™ Joint Adhesive and Corian® Joint Adhesive are the ONLY joint adhesives approved for making rigid bonds to Corian® Solid Surface products. Use these adhesives for inconspicuous seams between Corian® Solid Surface products.

A flexible bond between Corian® Solid Surface and Corian® Solid Surface or another material – A flexible bond that allows movement is required when bonding Corian® Solid Surface to other materials or when the design requires expansion. The flexibility of silicone adhesive allows movement due to thermal expansion or contraction. When bonding to substrates or support frames where the silicone will not be visible, 100% silicone adhesive is recommended. For visible expansion joints, either between Corian® products or to other materials such as adjoining walls, various colours of silicone sealant are available.

A temporary bond to hold surfaces of Corian® Solid Surface in place while the main adhesive system cures – Temporary bonds, either for adhering clamping blocks or for temporary adhesion while the main adhesive cures, can be useful. Hot-melt adhesive can be used for temporary bonds, but never for permanent bonding.

A. Safety

Please read the Safety Data Sheets (SDS) for these adhesives. The SDS documents include important safety information and may be found at <http://msds.dupont.com>.

B. Joint Adhesive

Colour-coordinated DuPont™ Joint Adhesive and Corian® Joint Adhesive are the only endorsed adhesives for creating an inconspicuous hard seam. They are produced in a range of specific colours to complement solid surface sheet and shape products. Some adhesive colours can be used with multiple colours of Corian® Solid Surface. Refer to suggested colour information. Exact colour match cannot be guaranteed.

DuPont™ Joint Adhesive and Corian® Joint Adhesive create a rigid bond and should only be used to bond Corian® Solid Surface to Corian® Solid Surface. Bonding Corian® Solid Surface to any other material, including other brands of solid surface should be done with flexible silicone adhesive/sealant except where explicitly approved by DuPont. Bonding Corian® brand Solid Surface sinks or basins to Corian® Quartz surfacing is an approved application.

Corian® Joint Adhesive and DuPont™ Joint Adhesive are provided in two sizes, 50 ml and 470 ml (bulk). All joint adhesive must be used by expiration date printed on the container.

Corian® Joint Adhesive cartridges can be stored either vertically or horizontally. On removal from storage Corian® Joint Adhesive may be used immediately.

For DuPont™ Joint Adhesive only: Long term storage of tubes should be with the cartridge on its side as this keeps the ingredients evenly distributed. No more than 30 minutes before use, the cartridge should be turned vertically upright with the plug sealing the cartridge at the top. This initial step will allow any air to rise to the top where it can be removed.

The adhesive will begin to cure as soon as it is mixed within the mixer tip. If not using the adhesive within five minutes (higher temperature will shorten this time) remove the mixer tip and replace the plug, taking care to wipe the opening carefully so the components are not mixed.

The adhesive should always be used by its expiration date as shown on the label. This varies by adhesive.

CORIAN® JOINT ADHESIVE

Daaaaaaaa COLOUR NAME
EXP: UKMMYY-nn
xxxxxxx yyyyyy

Daaaaaaaa	product code
MMYY-nn	expiration Month Year
xxxxxxx yyyyyy	batch number, cartridge number

Example label

D1553308 BISQUE
EXP: UK0420-16
1821621 000023

Bisque adhesive that expires last day of April 2020.

DUPONT™ JOINT ADHESIVE

Daaaaaaa COLOUR NAME	
EXP USMMYY-nnn MM/DD/YY	
xxxx	
Daaaaaaa	product code
USMMYY-nnn	expiration Month Year-manufacturing code
MM/DD/YY	production date (day/month/year)
xxxx	manufacturing code

Example label

D11971248 BONE
EXP US0519-015 04/22/17
1435

Bone adhesive that expires the last day of May 2019.

If needed, report the entire code to report quality issues.

HELPFUL HINTS

Follow all instructions attached to the cartridge. Pay particular attention to the safety and first aid details.

Do not use adhesive that is past the use by date.

Vehicles can reach excessive temperatures on hot sunny days. Make sure the adhesive stays cool while transporting it to the job site.

If the adhesive is cold, allow it to warm to room temperature before using.

When using a manual dispenser, simulate the constant pressure of an air powered dispenser. Changes in pressure from pressurising the cartridge will affect mixing and set time.

Adhesive cures faster in warmer temperatures. When applying adhesive in a warm room, be sure to have adequate help to clamp the pieces together before the glue begins to harden.

Always use lint free white cloths or white paper towels when using adhesive. The adhesive may extract dyes or pigments from coloured materials.

470 ml (bulk) Cartridges Preparation and Use

The following steps are essential to fully remove air and ensure the two components are properly mixed at the right ratios.

- **For DuPont™ Joint Adhesive only:** Let cartridge stand on end for about 30 minutes at room temperature before using. This allows any trapped air to rise to the top where it can be purged. Failure to perform this step may result in poor cure.
- **Corian® Joint Adhesive** may be used immediately
- **For all adhesives:** Place cartridge in dispenser. Remove retainer nut. Remove the grey chamber plug. Set plug aside for later use.

- Make sure the pressure regulator shows 0 bar (0 psi) before attaching the air hose.
- Connect dispenser to air source and adjust pressure. Note that DuPont™ Joint Adhesive and Corian® Joint Adhesive will have different optimum settings. **Start at 2 bar (29 psi) and adjust as needed. Do not extrude Corian® Joint Adhesive above 4.8 bar (70 psi) as this will result in poor cure.**

If the air line does not have a gauge, turn regulator knob on gun anticlockwise until it stops. Then turn knob about three full revolutions clockwise. Dispense a small test bead, then adjust as necessary.

- Hold end of cartridge over a paper cup. For DuPont™ Joint Adhesive the tip should be angled upwards to aid in air removal. The tip position is not important for Corian® Joint Adhesive. While pointing dispenser away from anyone, pull trigger to allow any air trapped inside cartridge to escape and to fill chambers with adhesive, ensuring the flow of each component is balanced. Release trigger. If using manual dispenser, squeeze handle slowly until air is gone and both chambers are full, then push tab on back of dispenser. **There may be more of one component, extrude until each component is coming out from each nozzle (adhesive components are then balanced).**
- Keeping cartridge upright, put mixer tip on cartridge and secure with retaining nut.

Mixer tips will only fit one way. Slip retainer nut over mixer tip and lock it securely in place by giving a quarter turn clockwise. The mixer tip fit is very snug. Be sure it is in proper position before use or leaking around the tip may occur.

- Keeping the dispenser angled upwards to aid air removal from the mixer tip, adjust pressure to desired setting and run out a 100 mm bead of adhesive onto a paper towel. By the end of the bead, the bead should be air free and uniform in colour. If necessary, extrude additional adhesive until uniform appearance is achieved. **Do not start seaming until extruded adhesive is air free and uniform in appearance.**
- Depending on the temperature of the room, the dispenser can be set down for approximately 5 minutes before a tip change is needed. Since the adhesive will cure faster in warmer temperatures, a tip change may be needed in less than 5 minutes if you're working in a hot environment.

Do not place curing adhesive in a bin. Allow adhesive to harden first.

- To remove cartridge from air dispenser, press red button on back of hand grip until piston is completely retracted. Press small black button on underside of dispenser housing to dislodge cartridge.
- To remove cartridge from manual dispenser, press lever behind handle and, retract the plunger manually. Press small black button on underside of dispenser housing to dislodge cartridge.
- To store unused portions, first remove cartridge from dispenser, remove retainer cap and discard mixer tip. Replace chamber plug in end of cartridge, screw on retainer nut to secure plug with slotted metal washer.

HELPFUL HINTS

If you have not used the entire cartridge and you wish to store for further use: remove the tip and retaining nut, wipe any residue with a white cloth or paper towel, seal the cartridge with the plug, replace the retaining nut and replace slotted washer.

The 470 ml (bulk) cartridge is equivalent to approximately 9 small tubes.

As the 470 ml (bulk) cartridge is normally used for large glue jobs, it is important that all preparation is complete before gluing commences.

The manual cartridge gun eliminates the need to use the air hose system as it works by hand pressure only. For best operation simulate the smooth continuous pressure of an air-operated dispenser.

50 ml Cartridges Preparation and Use

The following steps are essential to fully remove air and ensure the two components are properly mixed at the right ratios.

- **For DuPont™ Joint Adhesive only:** Let cartridge stand on end for approximately 30 mins at room temperature before using. This allows any trapped air to escape.
- **Corian® Joint Adhesive** may be used immediately.
- **For all adhesives:** Remove cap and save.
- Pointing cartridge up, place cartridge in dispenser and close the black latch. The cartridge only fits in one way.
- **Hold end of cartridge over a paper cup.** For DuPont™ Joint Adhesive the tip should be angled upwards to aid in air removal. The tip position is not important for Corian® Joint Adhesive. While pointing dispenser away from anyone, squeeze handle slowly to allow any air trapped inside cartridge to escape and to fill chambers with adhesive, ensuring the flow of each component is balanced. **There may be more of one component, extrude until each component is coming out from each nozzle (adhesive components are then balanced).**
- Install mixer tip and twist to lock in place.

Mixer tips will only fit one way. Line up the raised point on the mixer tip. The cap fits into the v-notch on cartridge. Spin the cap a quarter of a turn clockwise to lock the tip into place.

- Keeping the dispenser angled upwards to aid air removal from the mixer tip, squeeze dispenser handle slowly and dispense a bead about 6 mm wide and the length of the tip onto a paper towel or scrap piece of paper, cardboard, etc. By the end of the bead, the bead should be air free and uniform in colour. If necessary, extrude additional adhesive until uniform appearance is achieved. **Do not start seaming until extruded adhesive is air free and uniform in appearance.**

Do not place curing adhesive in a bin. Allow adhesive to harden first then dispose of properly.

- Depending on the temperature of the room the dispenser can be set down for approximately 5 minutes before a tip change is needed. Since the adhesive will cure faster in warmer temperatures, a tip change may be needed in less than 5 minutes if working in a hot environment.
- To remove cartridge from dispenser, press tab on back of dispenser and retract plunger and lift black latch.
- To store unused adhesive, remove tip wiping any residue with a white cloth or paper towel and replace cap.

DuPont™ Joint Adhesive and Corian® Joint Adhesive Storage

Adhesive should be stored in a well-ventilated room, in the dark. The recommended storage temperature range for DuPont™ Joint Adhesive and Corian® Joint Adhesive is 12-25°C.

Cartridges should be stored on their sides. Follow local regulations for flammable material storage. Use precautions during transport, as vehicles can rapidly reach elevated temperatures. Exposure to elevated temperatures will shorten shelf life. Do not store in a freezer.

Storing cartridges with the tip in place may cause blockage or curing of the adhesive within a cartridge. Always remove the tip and replace the plug for storage.

DuPont™ Joint Adhesive and Corian® Joint Adhesive Disposal

Storage, transportation and disposal must be in accordance with applicable regulations. Do not flush to surface water or sanitary sewer system. Do not incinerate in closed containers.

C. Flexible Adhesives/Sealants

A flexible bond that allows movement is required when bonding Corian® Solid Surface to other materials or when the design requires expansion. The flexibility of silicone adhesive allows movement due to thermal expansion or contraction. When bonding to substrates or support frames where the silicone will not be visible, 100% silicone adhesive is recommended. If there is a concern that the silicone may “show through”, such as with light colours of 6 mm Corian® sheets, then clear or translucent silicone may be the best colour choice. For visible expansion joints between Corian® surfaces or to other materials, such as adjoining walls, use a silicone adhesive/sealant in a colour that complements the solid surface colour.

Silicone cures by reacting with water in the air and exposure to air is required to cure. Avoid applying in large dabs or enclosed “picture frames” as this will cure slowly.

Cure is most rapid between 40-60% relative humidity (RH). Cure will be slower both at very high and very low humidity. While some bonding occurs quickly, full cure generally takes more than a week. If clamping or bracing is not practical, hot-melt adhesives may be used to hold the materials in place until the silicone cures.

As an alternative to silicone adhesives and sealants, MS Polymers or PU sealants can also be used.

All flexible adhesives require some bond thickness to allow movement. A 1.5 mm thickness would suffice for most flexible adhesives to ensure a flexible bond. They are best applied as a bead that retains some thickness after clamping. Larger pieces may require extra thickness.

D. Hot-Melt Adhesives

Hot-melt adhesives are useful for TEMPORARY bonds, either to hold material in place until the main adhesive cures or for bonding blocks for clamping. They should NEVER be used for permanent bonds. Use a hot-melt adhesive that is recommended for plastics. An “open” or “set” time of one minute is desirable. Hot-melt adhesives will cool quickly once they come in contact with Corian® Solid Surface.

PLEASE VISIT OUR WEB SITE: WWW.CORIAN.UK OR CONTACT YOUR CORIAN® REPRESENTATIVE FOR MORE INFORMATION ABOUT CORIAN® SOLID SURFACE.

This information is based on technical data that DuPont Specialty Products USA, LLC and its affiliates (“DuPont”) believe to be reliable, and is intended for use by persons having technical skill and at their own discretion and risk. DuPont cannot and does not warrant that this information is absolutely current or accurate, although every effort is made to ensure that it is kept as current and accurate as possible. Because conditions of use are outside DuPont’s control, DuPont makes no representations or warranties, express or implied, with respect to the information, or any part thereof, including any warranties of title, non-infringement of copyright or patent rights of others, merchantability, or fitness or suitability for any purpose and assumes no liability or responsibility for the accuracy, completeness, or usefulness of any information. This information should not be relied upon to create specifications, designs, or installation guidelines. The persons responsible for the use and handling of the product are responsible for ensuring the design, fabrication, or installation methods and process present no health or safety hazards. Do not attempt to perform specification, design, fabrication, or installation work without proper training or without the proper personal protection equipment. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents. DuPont shall have no liability for the use of or results obtained from such information, whether or not based on DuPont’s negligence. DuPont shall not be liable for (i) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and (ii) special, direct, indirect or consequential damages. DuPont reserves the right to make changes to this information and to this disclaimer. DuPont encourages you to review this information and this disclaimer periodically for any updates or changes. Your continued access or use of this information shall be deemed your acceptance of this disclaimer and any changes and the reasonableness of these standards for notice of changes.

Copyright© 2019 DuPont Specialty Products USA, LLC. The Corian® Solid Surface Logo and Corian® are trademarks of DuPont Specialty Products USA, LLC or its affiliates. All rights reserved.